

International Journal for Pharmaceutical Research Scholars (IJPRS)



ISSN No: 2277 - 7873

RESEARCH ARTICLE

Studies on Co-Ordination Polymers of 5,5'-(6-(4-Methoxy Phenoxy)-1,3,5-Triazine-2,4-Diyl)Bis(Azanediyl)Diquinolin-8-Ol

Talaviya P^{*1}, Chaudhari JA²

^{*1}Department of Chemistry, Research Scholar of JJT University, Rajasthan-333001.
 ²Shri R.K.Parikh Arts & Science College Petlad, Gujarat-388450.
 Manuscript No: IJPRS/V2/I2/00108, Received On: 28/05/2013, Accepted On: 03/06/2013

ABSTRACT

A novel is ligand namely 5,5'-(6-(4-methoxyphenoxy)-1,3,5-triazine-2,4-diyl)bis (azanediyl)diquinolin-8-ol (PBDQ-6) has been prepared and characterized. This ligand was characterized by IR, ¹H-NMR, and elemental analysis. Coordination polymers of this bis-ligand (NBDQ) were prepared with Cu(II), Ni(II), Co(II), Mn(II), and Zn(II) metal ions. All of these coordination polymers were characterized by elemental analyses, IR spectral and diffuse reflectance spectral studies. The thermal stability was evaluated by thermo gravimetric analyses (TGA). In addition, all of the coordination polymers have been characterized by their magnetic susceptibilities. All the novel synthesized compounds were screened for their antibacterial and antifungal activities.

KEYWORDS

5-Amino 8-hydroxyquinoline, antibacterial and antifungal activities, coordination polymers, IR, NMR, reflectance spectra and TGA.

INTRODUCTION

In recent years, the study on Co-ordination polymer has made much progress¹⁻³. 8quinolinol is well known as an analytical reagent^{4,5}. Its various derivatives are very useful in pharmaceuticals⁶. Several azo dyes based on 8-quinolinol are also reported for dyeing of textiles as well as their chelating properties^{7,8}. A promising method has been reported for the formation of coordination polymers of enhanced chelating ability by using a bidentate 8hydroxyquinoline moiety in which two 8hydroxyquinolinyl end groups are joined with bridge, usually at the 5,5'-position^{9–11}. The 5– Amino 8-hydroxy quinolinol is the easiest preparable precursor for the preparation of bis-

*Address for Correspondence: Purav Talaviya Department of Chemistry, Research Scholar of JJT University, Rajasthan-333001, India. E-Mail Id: pytalaviya@gmail.com ligand and thus bis-ligands based on 5–Amino 8–hydroxyquinoline have been reported for coordination polymers^{11,12}. Ion exchange resins have also been prepared from 5–amino 8– hydroxyquinoline and amino or hydroxyl functionalized polymers^{13,14}. We are also synthesized compound of PBDQ-6. Hence, In this paper, we report newly compound of in continuous of this work^{15,16}. The present paper deals with synthesis, characterization and chelating properties of ligand (PBDQ-6) and its co-ordination polymers are shown in Scheme 1.

Experimental

Materials

All the chemicals used were of pure grade. The synthesis 5,5'-(6-(4-methoxyphenoxy)-1,3,5-triazine-2,4-diyl) bis(azanediyl)diquinolin-8-ol (PBDQ-6) was carried out in two steps. 5–



Amino 8 -hydroxyl quinoline was prepared according to a literature method¹⁷.

Synthesis of 5,5'-(6-(4-methoxyphenoxy)-1,3,5triazine-2,4-diyl)bis(azanediyl) diquinolin -8-ol (PBDQ-6)

To a suspension of 5-amino 8-hydroxyquinoline 2.4-dichloro-6-(4-(3.2)mol). g, 0.02 methoxyphenoxy)-1,3,5-triazine (2.71 g, 0.01 mol) in an acetone-water mixture was added. Then K_2CO_3 (0.02 mol) was added as an acid accepted [18]. The resulting mixture was refluxed for 3 hr with occasional shaking. The resulting suspension. which contained a precipitate, was neutralise and then filtered. The solid product was collected and dried to give PBDQ-6 (68% yield). The product melted with decomposition at above 242^oC (uncorrected).

Synthesis of Coordination Polymer

A solution of metal (0.01 mol) in aqueous formic acid was added drop wise to a solution of PBDQ-6 (0.01 mol) in aqueous formic acid with stirring. The reaction mixture was heated on a water bath for 0.5 hr. The reaction mixture was made alkaline by the addition of dilute aqueous ammonia until the precipitation was completed. The polymer separated out in the form of a suspension and was digested on a boiling water bath for about 1 hr. Finally, the resultant solid was collected by filtration and washed with hot water, dimethylformamide (DMF), and then acetone. The polymer [PBDQ-6-M⁺²] (resultant product) was air-dried.

Antimicrobial Activities

Antibacterial activity and antifungal activities of PBDQ-6 ligand and its coordination polymers were studied against gram-positive bacteria (Bacillus subtilis and staphylococcus aureus) and gram-negative bacteria (E.coli, salmonella typhi and klebsiella promioe) and plant pathogenic organisms used were Aspergillus albicans, niger. Candida *Trichoderma* harsianum., Mucor mucedo., and Botrytis *cinerea* at a concentration of 50 μ g/ml by agar cup 520 plate method. The methanol system was used as control in this method. The area of inhibition of zone was measured in mm.

Measurement

The C, H, N contents of metal were determined by TF-Flash-1101 EA. The metals contents of metal chelates were determined volumetrically by Vogel's method¹⁹. To a 100mg chelate sample, 1ml of HCl, H₂SO₄ and HClO₄ each were added and then 1 gm of NaClO₄ was added. The mixture was evaporated to dryness and the resulting salt was dissolved in double distilled water and diluted to the mark. From this solution the metal content was determined by titration with standard EDTA solution. Infrared spectra of the synthesized compounds were recorded on Nicolet 760 FT-IR spectrometers. NMR spectrum of ligand was recorded on a Brucker spectrophotometer at 400 MHz. Magnetic susceptibility measurement of the synthesized coordination polymer was carried out on Gouy Balance at room temperature. The electronic spectra of coordination polymer in solid were recorded at room temperature. MgO was used as a reference. Antimicrobial activity of all the samples was monitored against various gram positive (+) and gram negative (-) organisms, following the method reported in the literature_{20,21}.

RESULTS AND DISCUSSION

The synthesis bis-ligand of 5,5'-(6-(4methoxyphenoxy)-1,3,5-triazine-2,4-diyl) bis (azanediyl)diquinolin-8-ol (PBDQ-6) was performed by a simple nucleophilic substitution reaction of ,4-dichloro-6-(4-methoxyphenoxy)-1,3,5-triazine and 5-amino 8-hydroxy quinoline. The resulting PBDQ-6 ligand was an amorphous colour powder. The ligand is characterized by elemental analysis as well as ¹H NMR and IR spectroscopic techniques as given below.

Elemental Analysis

The analytical and physical properties of the ligand and its coordination polymers are listed in Table-1. The metal and C, H, N contents of bis-ligand and coordination polymer (its coordination polymer) are shown in Table-1 and are also constent with the predicted structure.

Empirical	Mol. Cal	Viold	Elemental Analysis (%) Found(Calcd)			
Formula	g/mol					
		70	С	н	Ν	М
C ₂₈ H ₂₁ N ₇ O ₄	519	65	64.6(64.73)	4.0(4.04)	18.8(18.88)	
C ₂₈ H ₁₉ N ₇ O ₄ Cu ⁺² .2H ₂ O	616.5	66	54.5(54.50)	3.7(3.73)	15.8(15.89)	10.3(10.30)
C ₂₈ H ₁₉ N ₇ O ₄ Ni ⁺² .2H ₂ O	608	70	55.2(55.26)	3.7(3.78)	16.1(16.11)	9.0(9.04)
$C_{28}H_{19}N_7O_4 Co^{+2}.2H_2O$	612	70	54.8(54.90)	3.7(3.75)	16.0(16.01)	9.6(9.64)
C ₂₈ H ₁₉ N ₇ O ₄ Mn ⁺² .2H ₂ O	612	63	54.9(54.90)	3.7(3.75)	16.0(16.01)	9.6(9.64)
C ₂₈ H ₁₉ N ₇ O ₄ Zn ⁺² .2H ₂ O	618	65	54.3(54.36)	3.6(3.72)	15.8(15.85)	10.5(10.51)

Table 1: Analysis of PBDQ-6 ligand and its metal chelates

Table-2: Spectral feactures and magnetic moment of metal chelates

Metal Chelates	μ _{eff} BM	Electronic Spectral Data cm ⁻¹	Transitions	IR spectral feactures Common for all cm ⁻¹
PBDQ-6 -Cu ⁺²	1.73	24385 15622	$C.T$ ² Eg \rightarrow ² T ₂ g	1602 Quinoline Moiety 1508,
PBDQ-6 -Ni ⁺²	2.82	24116 15192 8000	${}^{3}A_{2}g \rightarrow {}^{3}T_{1}g(P)$ ${}^{3}A_{2}g \rightarrow {}^{3}T_{1}g(F)$ ${}^{3}A_{2}g \rightarrow {}^{3}T_{2}g$	1427, 1481 3450, 3550 -NH
PBDQ-6 -Co ⁺²	4.87	24125 19720 8669	${}^{4}T_{1}g(F) \rightarrow {}^{4}A_{2}g$ ${}^{4}T_{1}g(F) \rightarrow {}^{4}T_{1}g(P)$ ${}^{4}T_{1}g(F) \rightarrow {}^{4}T_{2}g$	3800-2600 broad OH- phenolic 1090, 1280 C-O-M (Stretching)
PBDQ-6 -Mn ⁺²	5.91	23975 17644 15468	${}^{6} A_{1}g \rightarrow {}^{6}A_{1}g ({}^{4}Eg)$ ${}^{6} A_{1}g \rightarrow {}^{4}T_{2}g ({}^{4}G)$ ${}^{6} A_{1}g \rightarrow {}^{4}T_{1}g ({}^{4}G)$	1220 O-M 550 M-N 490
PBDQ-6 -Zn ⁺²	Diamagnetic			

The results show that the metal: ligand (M: L) ratio for all divalent metal chelate is 1:1.

IR Analysis

The important infrared spectral bands and their tentative assignments for the synthesized ligand H_2L and its coordination polymers were recorded as KBr disks and are shown in Table-2.

IR spectrum of ligand of PBDQ-6 show a broad band extended from 3800 to 2600 cm⁻¹ which might be responsible to phenolic -OH group bonded to N atom of 8-hydroxyquinoline moieties²².

Several bands appeared between 1500 and 1600 cm⁻¹ region may arised from aromatic breathing and 3450 to 3550 cm⁻¹ for -NH group. The IR band at 1580 cm⁻¹ (C=N of 8-quinolinol system) of PBDQ-6 ligand shifted to higher frequency side 1600 cm⁻¹ in the spectra of the metal complexes indicating involvement of nitrogen in the complexes formation²³, whereas the band at 1220 cm⁻¹ in the IR spectrum of PBDQ-6 assigned to in-plane –OH deformation was shifted towards higher frequency in the spectra of the coordination polymer due to the formation of the M–O bond²⁴. This was further confirmed by a weak band at 1090 cm⁻¹ corresponding to C-O-M stretching, while bands around 550 and 490 cm⁻¹ correspond to the $M \rightarrow N$ vibration²⁵.

¹H NMR Analysis

The structural analysis of the ligand (PBDQ-6) was determined by ¹H NMR spectrum.

NMR (DMSO)

6.8 – 8.8 ppm (14H)	Multiplet Aromatic
5.3 ppm (1H)	Singlet (OH)

4.0 nnm (1H)	Singlet (NH)
4.0 ppm (1 n)	Singlet (INT)

Magnetic Measurements

Magnetic moments of coordination polymers are given in Table-2. The diffuse electronic spectrum of Cu⁺²complex shows two broad bands 15622 and 24385cm⁻¹. The first band may be due to a ${}^{2}\text{Eg} \rightarrow {}^{2}\text{T}_{2}\text{g}$ transition, while the

second band may be due to charge transfer. The first band shows structures suggesting a distorted octahedral structure for the Cu⁺² metal $complex^{26,27}$. The Co⁺² metal complex gives rise to two absorption bands at 21270 cm⁻¹, 18700 cm⁻¹ and 11500 cm⁻¹ which can be assigned ${}^{4}T_{1}g(F) \rightarrow {}^{4}A_{2}g$ ${}^{4}T_{1}g(F) \rightarrow {}^{4}T_{1}g(P)$ and ${}^{4}T_{1}g(F) \rightarrow {}^{4}T_{2}g$ transitions, respectively. These absorption bands and the μ_{eff} value indicate octahedral configuration of the Co⁺² metal complex^{28,29}. The spectrum of Mn⁺² polymeric complex comprised three bands at 24125cm⁻¹, 19720cm⁻¹ and 8669 cm⁻¹. These bands may be assigned to ${}^{6}A_{1}g \rightarrow {}^{6}A_{1}g({}^{4}Eg), {}^{6}A_{1}g \rightarrow {}^{4}T_{2}g({}^{4}G)$ and ${}^{6}A_{1}g \rightarrow {}^{4}T_{1}g({}^{4}G)$ transitions, respectively. The high intensity of the bands also suggests that they may have some charge transfer character. The magnetic moment is found to be lower than normal range. In the absence of low temperature measurement of magnetic moment, it is difficult to attach any significance to this. As the spectrum of the metal complex of Ni⁺² show three distinct bands at 24116cm⁻¹, 15192cm⁻¹ and 8000 cm⁻¹ are assigned as ${}^{3}A_{2}g \rightarrow {}^{3}T_{1}g(P)$, ${}^{3}A_{2}g \rightarrow {}^{3}T_{1}g(F)$ and ${}^{3}A_{2}g \rightarrow {}^{3}T_{2}g$ transition, respectively, suggesting the octahedral environment for Ni⁺² ion. The observed μ_{eff} values in the range 1.73–5.91 B.M are consistent with the above moiet $y^{30,31}$.

Thermal Studies

The TGA data for the Co-ordination polymers samples at different temperatures indicate that the degradation of the co-ordination polymers is noticeable beyond 390° C. The rate of degradation becomes a maximum at a temperature between 410 and 490° C. This may be due to acceleration by metal oxides, which form in situ. Each polymer lost about 60% of its weight when heated up to 700° C. Inspection of the thermograms of all coordinated polymer samples revealed that all samples suffered appreciable weight loss in the range of 150 to 290° C. This may be due to the presence of a coordinated water molecule.

Antimicrobial Activities

The antibacterial and antifungal data obtained from analysis are shown in Table-3 and Table-

4, respectively. The increase in antimicrobial activity may be considered in light of Overtone's concept³² and Tweedy's chelation theory³³. According to Overtone's concept of cell permeability, the lipid membrane that surrounds the cell favors the passage only of lipid-soluble materials due to which liposolubility is an important factor controlling the antimicrobial activity. On complexation, the polarity of the metal ion will be reduced to a greater extent due to the overlap of the ligand orbital and partial sharing of the positive charge of the metal ion with donor groups. Further, it increases the delocalization of -electrons over the whole chelate ring and enhances the lipophilicity of the coordination polymers. This increased lipophilicity enhances the penetration the coordination polymer into of lipid membranes and blocks the metal binding sites in of microorganisms. the enzymes These polymers also disturb coordination the respiration process of the cell and thus block the synthesis of proteins, which restricts further growth of the organisms. Coordination polymers exhibit higher biocidal activity as compared with the free ligands; from the comparative analysis shown in Table-3 and Table-4. respectively, it is observed that all the coordination polymer are more potent biocidals than the free ligands.

From the data obtained it is clear that Cu (II) is highly active among the coordination polymer of the respective metal.

CONCLUSION

The present work in the conclusions with coordinaly polymer based of bis-8HQ has been performed successfully. Through bis-8HO versatile pharmaceutical active molecule. A series of coordination polymers from these bisligands with transition metals have been prepared and characterized for their spectral and magnetic properties. All the synthesized coordination polymers were monitored for their antimicrobial activity. The coordination polymers are toxic for gram-negative bacteria (E.coli, samonella typhi and klebsiella promioe) and gram-positive bacteria (Bacillus subtilis and staphylococcus aureus), and plant pathogenic organisms (fungi) used were Aspergillus niger, Candida albicans. Trichoderma harsianum, Mucor mucedo. and Botrytis cinerea microorganisms. found It is that the coordination polymers were more toxic for one or more bacterial strains, thus introducing a novel class of metal-based bactericidal agents. The information as octahedral geometry of the coordination polymer was obtained from their electronic and magnetic moment values.

	G	Fram +ve	Gram –ve		
Compounds	Bacillus Subtilis	Staphylococcus Aureus	klebsiella promioe	Salmonella Typhi	E.coli
PBDQ-6	23	20	20	22	23
(Cu PBDQ-6 (H ₂ O) ₂) _n	32	30	30	32	27
(Co PBDQ-6 (H ₂ O) ₂) _n	32	28	20	25	24
(Ni PBDQ-6 (H ₂ O) ₂) _n	30	26	24	22	26
$(Mn PBDQ-6 (H_2O)_2)_n$	30	31	28	23	22
(Zn PBDQ-6 (H ₂ O) ₂) _n	30	28	30	32	22

 Table 3: Antibacterial activity of coordination Polymers

	Zone of Inhibition at 1000 ppm (%)					
Compounds	Aspergillus Niger	Candida albicans	Trichoderma harsianum	Mucor mucedo	Botrytis cinerea	
PBDQ-6	23	27	25	28	24	
(Cu PBDQ-6 (H ₂ O) ₂) _n	32	35	45	30	22	
(Co PBDQ-6 (H ₂ O) ₂) _n	20	32	27	27	30	
(Ni PBDQ-6 (H ₂ O) ₂) _n	30	25	32	26	25	
(Mn PBDQ-6 (H ₂ O) ₂) _n	30	29	32	28	30	
(Zn PBDQ-6 (H ₂ O) ₂) _n	24	26	31	27	32	

Table 4: Antifungal activity of coordination Polymers

ACKNOWLEDGEMENT

We are grateful to the Principal, Shri R. K. Parikh Arts and Science College Petlad for providing the necessary research facilities.

REFERENCES

- Sherman S, Ganon J, Buchi G, Howell KO, Eneyel WR, Chem. Tech., Epoxy Resins, John Wiley Inc., New York, 1980, (9), 267.
- 2. Freeman HS, Esancy JF, Colour Chemistry, Elsever, London and New York. 1991.
- 3. Smolin EM, Rapopret L, S-Triazine and Derivatives, Interscience, New York. 1954.
- 4. Vogel's AI, A Textbook of Quantitative Chemical Analysis, Revised by Besselt J, Denny RC, Jeffery JH, Mendham J, ELBS Ed., 1996, 5.
- 5. Ivanor VM, Metkina TF, Ah. Anal Khim, 1978, 33, 2426.
- 6. Burckhalter JH, Stephars VC, Searberough HC, Briniger WS, Edergton WE, J. Am. Chem. Soc. 1954, 76, 4902.
- 7. Vogel C, Heinz W, Brazil Pat, 1977, 78, 05.
- 8. Burckhalter JH, Leib R, Eswaran. J. Org. Chem. 1961, 26, 4078.

- 9. Horowitz H, Perros JP, J. Inorg. Nucl. Chem. 1964, 26, 139.
- 10. Bailer JR, Judd CJ, McLean ML, M.J. Coordination Polymers (WADC Technical Reports), 1959, 116, 58–51.
- 11. Patel RD, Patel SR, Patel HS, Eur. Polym. J. 1987, 23, 229.
- 12. Shah TB, Patel HS, Dixit RB, Dixit BC, Int. J. Polym. Anal. and Charact, 2003, 8, 369.
- 13. Xian Ren C, Yuqi F, Hisanori I, Kazuhisa H, Kousaburo O, Analytical Sci., 1995, 11, 313.
- Abraham W, Abraham D, Guy R, Abraham, P, Reactive Polymers, Ion Exchangers, Sorbents. 1984, 2, 301.
- 15. Talaviya PV, Chaudhari JA, Int. Journal of Chemical, Biological and Physical Sciences, 2012, 1, 109.
- 16. Talaviya PV, Chaudhari JA, Der Pharma Chemica, 2013, 5(2), 157-162.
- 17. Patel KD, Pachani SC, Dixit RB, Int. J. Inorganic and Orgeno Metallic Polymers 2003.
- 18. Patel HS, Patel VK, Indian J. Hetrocycl Chem. 2003, 12, 253.

- 19. Vogel AI, Textbook of Quantitative Chemical Analysis, 4th ed., ELBS: London, 1978.
- 20. Murrey PR, Baran EJ, Pfuller MA, Tenovov FC, Yolken RH, An Antimicrobial Agent and Susceptibility Testing; Americal Soc. Microbiology: Washington, DC, 1995, 1327.
- 21. Phillips JP, Elbinger RL Merritt LL, J Am Chem Soc., 1949, 71, 3984.
- 22. Bellamy LJ, Infrared Spectra of Coordination polymer Molecules, Chapman and Hall, London, 1957.
- 23. Parekh HM, Panchal PK, Patel MN, J. Therm. Anal. Cal. 2006, 86, 803.
- 24. Masoud MS, Amira MF, Ramadan AM, ElAshry GM, Spectrochim. Acta, Part A 2008, 69, 30.
- 25. Satpathy KC, Pande AK, Mishra R, Panda I, Synth. React. Inorg. Met. Org. Chem. 1991, 21, 531.

- 26. Hathway BJ, Tomilson AAG, Coord Chem. Rev. 1980, 5, 1.
- 27. Pancholi HB, Patel MM, J. Polym. Mater. 1996, 13, 261–267.
- 28. Papplardo R, J. Chem. Phys. 1960, 33, 613.
- 29. Lewis J, Wilkins RS, Modern Coordination Chemistry; New York, 1960, 290.
- Figgis BN, Lewis J, The Magneto Chemistry of Coordination polymer in Modern Coordination Chemistry, Interscience, New York, 1960.
- 31. Williams JO, Adv Phys Org Chem., 1979, 15, 159.
- 32. Patel IJ, Vohra IM, E Journal of Chemistry, 2006, 3(2), 110-116.
- 33. Tweedy BG, Phytopathology 1964, 55, 910.